

Material: EN G24Mn6

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Mild Steel Alloys

Sub Group: EN G24Mn6 Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.250	Normalizing or Quenching or Solution Annealing	
Silicon	Si %	0.600 max.		
Manganese	Mn %	1.500 - 1.800		
Phosphorus	P %	0.020 max.		
Sulphur	S %	0.015 max.		
Chromium	Cr %	0.300 max.		
Molybdenum	Mo %	0.150 max.		
Nickel	Ni %	0.400 max.		
Copper	Cu %	0.300 max.		
Vanadium	V %	0.050 max.		
Iron	Fe %	Balance	Mechanical Properties Tensile Strength in Mpa 600 - 800 Yield Strength in Mpa 400 min. Elongation in % 12 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 27 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN 10213 G24Mn6	BS	British	Plate, Tubes and Forging
G24Mn6	AFNOR NF	France	Casting
G24Mn6	DIN	Germany	Casting
G24Mn6	UNI	Italy	Casting
G24Mn6	PN	Poland	Casting
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com