

Material: EN GX 23 CrMoV 12 1

Standard Specification for Steel Castings for Pressure Purposes

Group: Ferrous Stainless Steel Alloys

Sub Group: EN GX 23 CrMoV 12 1 Steel Castings for Pressure Purposes

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.200 - 0.260	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.030 max.		
Sulphur	S %	0.020 max.		
Chromium	Cr %	11.300 - 12.200		
Molybdenum	Mo %	1.000 - 1.200		
Nickel	Ni %	0.100 max.		
Vanadium	V %	0.250 - 0.350		
Tungsten	W %	0.500 max.		
			Mechanical Properties	
Copper	Cu %	0.300 max.	Tensile Strength in Mpa	740 - 880
Iron	Fe %	Balance	Yield Strength in Mpa	540 min.
-	-	-	Elongation in %	15 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	27 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4931	EN	European Union	Casting
1.4931	DIN	Germany	Casting
1.4931	DIN	Germany	Casting
GX23CrMoV12-1	AFNOR NF	France	Casting
G-X22CrMoV121	ONORM	Australia	Casting
OTA23VMoCr120	STAS	Romania	Casting
GX23CrMoV12-1	UNI	Italy	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com