

# Material: EN X 2 CrNiMo 17 12 3

## Standard Specification for Seamless Steel Tubes for Pressure Purposes

**Group:** Ferrous Stainless Steel Alloys

**Sub Group:** EN X 2 CrNiMo 17 12 3 Seamless Steel Tubes for Pressure Purposes

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Steel, Rod, Bar and Extrusion

Chemical Composition		
Carbon	C %	0.030 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.045 max.
Sulphur	S %	0.030 max.
Chromium	Cr %	16.500 - 18.500
Nickel	Ni %	10.500 - 13.000
Molybdenum	Mo %	2.500 - 3.000
Nitrogen	N %	0.110 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
Solution Annealing	

Mechanical Properties	
Tensile Strength in Mpa	490 - 2100
Yield Strength in Mpa	190 min.
Elongation in %	20 min.
Reduction of Area in %	63 min.
Hardness in HB	215 max.
Impact in Joule	60 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-5 EN 1.4436	BS	British	Tube
1.4436	DIN	Germany	Steel
1.4436	EN	European Union	Steel
X3CrNiMo17 13 3	UNI	Italy	Steel, Sheet, Plate and Strip
X3CrNiMo17 13 3	AFNOR NF	France	Steel
X3CrNiMo17 13 3	DIN	Germany	Sheet, Plate and Strip
316	SAE	USA	Steel, Wire, Bar, Shape and Forging

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India