

# Material: EN X 3 CrNiMoBN 17-13-3

## Standard Specification for Seamless Steel Tubes for Pressure Purposes

**Group:** Ferrous Stainless Steel Alloys

**Sub Group:** EN X 3 CrNiMoBN 17-13-3 Seamless Steel Tubes for Pressure Purposes

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Steel

Chemical Composition		
Carbon	C %	0.040 max.
Silicon	Si %	0.750 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.035 max.
Sulphur	S %	0.015 max.
Chromium	Cr %	16.000 - 18.000
Molybdenum	Mo %	2.000 - 3.000
Nickel	Ni %	12.000 - 14.000
Boron	B %	0.0015 - 0.0050
Nitrogen	N %	0.100 - 0.180
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
	Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	550 - 780
Yield Strength in Mpa	260 min.
Elongation in %	30 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	60 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
10216-5 EN 1.4910	BS	British	Tube
1.491	DIN	Germany	Steel and Flat
1.491	EN	European Union	Steel and Flat
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India