

Material: GOST 40 CH 24 N 12 SL

Standard Specification for Alloy steel casting

Group: Ferrous Stainless Steel Alloys

Sub Group: GOST 40 CH 24 N 12 SL Alloy steel casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.400 max.	As - Cast	
Silicon	Si %	0.500 - 1.500		
Manganese	Mn %	0.300 - 0.800		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	22.000 - 26.000		
Nickel	Ni %	11.000 - 13.000		
Copper	Cu %	0.300 max.		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 440 min. Yield Strength in Mpa 230 min. Elongation in % 7 min. Reduction of Area in % - Hardness in BHN - Impact in Joule 45 J @ RT	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4837	DIN	Germany	Casting
309C30	BS	British	Casting
SCH 13 A	JIS	Japan	Casting
422936	CSN	Czech Republic	Casting
J93503	UNS	USA	Casting
40 CrNiSi 25-12	MSZ	Hungary	Casting
A297 Grade HH	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com