

# Material: IS 10569 CuAl7Fe3Sn

## Standard Specification for Aluminium Bronze Rods, Bars and Sections

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** IS 10569 Aluminium Bronze Rods, Bars and Sections

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Rod, Bar and Section

Chemical Composition		
Lead	Pb %	0.050 max.
Tin	Sn %	0.200 - 0.500
Silicon	Si %	0.100 max.
Nickel	Ni %	0.250 max.
Magnesium	Mg %	0.050 max.
Zinc	Zn %	0.100 max.
Manganese	Mn %	0.250 max.
Iron	Fe %	2.000 - 3.000
Aluminium	Al %	6.000 - 7.500
Other	Ot%	0.250 max.
Copper	Cu %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
	As Raw or Annealing

Mechanical Properties	
Tensile Strength in Mpa	540 min.
Yield Strength in Mpa	240 min.
Elongation in %	25 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India