

# Material: IS 11286 Grade 3

## Standard Specification for Castings, Iron-Chromium, Iron-Chromium-Nickel Corrosion Resistant, for General Application

**Group:** Non-Ferrous Nickel Alloys

**Sub Group:** IS 11286 Grade 3 Castings, Iron-Chromium, Iron-Chromium-Nickel Corrosion Resistant, for General Application

**Application:** Intended for Valve, Pump, General Engineering, Automotive and other Industries

**Grade Belongs to the Industry:** Casting

Chemical Composition		
Carbon	C %	1.000 max.
Silicon	Si %	2.000 max.
Manganese	Mn %	1.150 max.
Phosphorus	P %	0.030 max.
Molybdenum	Mo %	3.000 max.
sulphur	S %	0.030 max.
Copper	Cu %	1.250 max.
Nickel	Ni %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
As-Cast or Annealing or Age Hardning	

Mechanical Properties	
Tensile Strength in Mpa	345 min.
Yield Strength in Mpa	120 min.
Elongation in %	9 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India