

Material: IS 13505 Grade 14

Standard Specification for Castings, Iron-Chromium, Iron-Chromium-Nickel Corrosion Resistant, for General Application

Group: Non-Ferrous Cobalt Alloys

Sub Group: IS 13505 Grade 14 Castings, Iron-Chromium, Iron-Chromium-Nickel Corrosion Resistant, for General Application

Application: Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.350 - 0.750	As-Cast or Annealing or Age Hardning	
Silicon	Si %	2.500 max.		
Manganese	Mn %	2.000 max.		
Chromium	Cr %	17.000 - 21.000		
Molybdenum	Mo %	0.500 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.050 max.		
Nickel	Ni %	37.000 - 41.000		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	450 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	4 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A 297 Grade HU	ASTM	USA	Casting
N08004	UNS	USA	Casting
J95405	UNS	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com