

# Material: IS 3444 Grade 23

## Standard Specification for Castings, Iron-Chromium, Iron-Chromium-Nickel Corrosion Resistant, for General Application

**Group:** Non-Ferrous Nickel Alloys

**Sub Group:** IS 3444 Grade 23 Castings, Iron-Chromium, Iron-Chromium-Nickel Corrosion Resistant, for General Application

**Application:** Intended for Valve, Pump, General Engineering, Automotive and other Industries

**Grade Belongs to the Industry:** Casting

Chemical Composition		
Carbon	C %	0.120 max.
Silicon	Si %	1.000 max.
Manganese	Mn %	1.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max.
Chromium	Cr %	1.000 max.
Copper	Cu %	26.000 - 33.000
Vanadium	V %	0.600 max.
Cobalt	Co %	2.500 max.
Iron	Fe %	6.000 max.
Nickel	Ni %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
As-Cast or Annealing or Age Hardning	

Mechanical Properties	
Tensile Strength in Mpa	500 min.
Yield Strength in Mpa	320 min.
Elongation in %	6 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India