

Material: IS 4522 Grade 13

Standard Specification for Heat Resistant Alloy Steel and Nickel Base Castings

Group: Ferrous Stainless Steel Alloys

Sub Group: IS 4522 Grade 13 Heat Resistant Alloy Steel and Nickel Base Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.350 - 0.750
Silicon	Si %	2.500 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.050 max.
Sulphur	S %	0.050 max.
Chromium	Cr %	17.000 - 21.000
Nickel	Ni %	37.000 - 41.000
Molybdenum	Mo %	0.500 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As - Cast or Annealing

Mechanical Properties	
Tensile Strength in Mpa	450 - 470
Yield Strength in Mpa	240 - 270
Elongation in %	3.5 - 4
Reduction of Area in %	-
Hardness in HB	135 - 210
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
N08004	UNS	USA	Casting
N08050	UNS	USA	Casting
A608 Grade HT 50	ASTM	USA	Casting
G X 40 NiCrSiNb 38-18	DIN	Germany	Casting
1.4849	DIN	Germany	Casting
N08005	UNS	USA	Casting
A297 Grade HT	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India