

## Material: IS 617 5230

### Standard Specification for Aluminium and Aluminium Alloys Ingot and Casting for General Engineering Purposes

**Group:** Non-Ferrous Aluminium Alloy

**Sub Group:** IS 617 Aluminium and Aluminium Alloys Ingot and Casting for General Engineering Purposes

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Ingot and Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.100 max.	As-Cast	
Magnesium	Mg %	3.000 - 6.000		
Silicon	Si %	0.300 max.		
Iron	Fe %	0.600 max.		
Manganese	Mn %	0.300 - 0.700		
Nickel	Ni %	0.100 max.		
Zinc	Zn %	0.100 max.		
Lead	Pb %	0.050 max.		
Tin	Sn %	0.050 max.		
Titanium	Ti %	0.200 max.		
Aluminium	Al %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LM5	BS	British	Ingot and Casting
EN AC-51300	AFNOR NF	France	Ingot and Casting
EN AC-51300	DIN	Germany	Ingot and Casting
EN AC-51300	ONORM	Australia	Ingot and Casting
EN AC-51300	EN	European Union	Ingot and Casting
EN AC-51300	BDS	Bulgaria	Ingot and Casting
-	-	-	-

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)