

## Material: IS 6912 7% Al Bronze FAB1

### Standard Specification for Copper and Copper Alloy Forging Stock and Forgings

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** IS 6912 Copper and Copper Alloy Forging Stock and Forgings

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Forging

Chemical Composition			Heat Treatment	
Lead	Pb %	0.050 max.	As Raw	
Tin	Sn %	0.100 max.		
Manganese	Mn %	0.500 max.		
Magnesium	Mg %	0.050 max.		
Nickel	Ni %	0.500 max.		
Iron	Fe %	2.000 - 3.500		
Silicon	Si %	0.150 max.		
Zinc	Zn %	0.400 max.		
Other	Ot%	0.500 max.		
Aluminium	Al %	6.500 - 8.000		
Copper	Cu %	Balance	<b>Mechanical Properties</b> Tensile Strength in Mpa 460 min. Yield Strength in Mpa - Elongation in % 30 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)