

Material: IS 8362 Aluminium Brass

Standard Specification for Copper and Copper Alloy Rolled Plates for Condensers and Heat Exchangers

Group: Non-Ferrous Copper Alloy

Sub Group: IS 8362 Copper and Copper Alloy Rolled Plates for Condensers and Heat Exchangers

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Plate

Chemical Composition			Heat Treatment	
Iron	Fe %	0.060 max.	As Raw	
Arsenic	As %	0.020 - 0.100		
Lead	Pb %	0.070 max.		
Aluminium	Al %	1.800 - 2.500		
Other	Ot%	0.300 max.		
Copper	Cu %	76.000 - 79.000		
Zinc	Zn %	Balance		
-	-	-	Mechanical Properties Tensile Strength in Mpa 280 min. Yield Strength in Mpa - Elongation in % 36 min. Reduction of Area in % - Hardness in BHN - Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com