

Material: ISO 121 Mg-Al8Zn1

Standard Specification for Magnesium-Aluminium-Zinc Alloy Casting

Group: Non-Ferrous Magnesium-Aluminium-Zinc Alloy

Sub Group: ISO 121 Magnesium-Aluminium-Zinc Alloy Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Bar and Wire

Chemical Composition		
Zinc	Zn %	0.300 - 2.000
Manganese	Mn %	0.150 min.
Silicon	Si %	0.500 max.
Iron	Fe %	0.050 max.
Copper	Cu %	0.350 max.
Nickel	Ni %	0.020 max.
Aluminium	Al %	7.000 - 9.500
Magnesium	Mg %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Solution Treated

Mechanical Properties	
Tensile Strength in Mpa	140 min.
Yield Strength in Mpa	75 min.
Elongation in %	-
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
MgAl8Zn1 Class 2A	JIS	Japan	Casting
MAG 7	BS	British	Ingot and Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India