

Material: ISO 17615 AlSi17Cu4Mg

Standard Specification for Aluminium and Aluminium Alloys Ingot and Casting

Group: Non-Ferrous Aluminium Alloy

Sub Group: ISO 17615 Aluminium and Aluminium Alloys Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	4.000 - 5.000	As-Cast	
Iron	Fe %	1.000 max.		
Magnesium	Mg %	0.450 - 0.650		
Manganese	Mn %	0.500 max.		
Nickel	Ni %	0.300 max.		
Silicon	Si %	16.000 - 18.000		
Tin	Sn %	0.300 max.		
Zinc	Zn %	1.500 max.		
Aluminium	Al %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	200 - 295
			Yield Strength in Mpa	180 - 260
			Elongation in %	1 min.
			Reduction of Area in %	-
			Hardness in HB	90 - 125
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LM30	BS	British	Ingot and Casting
390.0	AA	USA	Casting
ADC 14	JIS	Japan	Casting
AC-48100	EN	European Union	Casting
EN AC-48100	DIN	Germany	Casting
ALDC 14	JIS	Japan	Casting
EN AC-48100	UNE	Spain	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com