

Material: ISO 34 CrMo 4 E

Standard Specification for Mild Steel Alloys Bar and Rod

Group: Ferrous Mild Steel Alloys

Sub Group: ISO 34 CrMo 4 E Mild Steel Alloys Bar and Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.300 - 0.370	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.600 - 0.900		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	0.900 - 1.200		
Molybdenum	Mo %	0.150 - 0.300		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	590 min.
-	-	-	Yield Strength in Mpa	550 min.
-	-	-	Elongation in %	11 min.
-	-	-	Reduction of Area in %	59 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	25 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
34CrMo4	EN	European Union	Bar and Rod
1.722	EN	European Union	Bar and Rod
34CrMoS4	EN	European Union	Bar and Rod
1.7226	EN	European Union	Bar and Rod
P 880 - 34CrMo4	AFNOR NF	France	Bar and Rod
CMo 3 Z	MSZ	Hungary	Bar and Rod
34 CrMo 4 E	JIS	Japan	Bar and Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com