

Material: ISO 3522 Al Mg3

Standard Specification for Aluminium and Aluminium Alloys

Group: Non-Ferrous Aluminium Alloy

Sub Group: ISO 3522 for Aluminium and Aluminium Alloys

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Silicon	Si %	0.550 max.	As-Cast	
Iron	Fe %	0.550 max.		
Copper	Cu %	0.100 max.		
Manganese	Mn %	0.450 max.		
Magnesium	Mg %	2.500 - 3.500		
Zinc	Zn %	0.010 max.		
Titanium	Ti %	0.200 max.		
Other	Ot%	0.150 max.		
Aluminium	Al %	Balance		
-	-	-	Mechanical Properties	
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	140 min.
			Yield Strength in Mpa	70 min.
			Elongation in %	3 min.
			Reduction of Area in %	-
			Hardness in HBW	50 min.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-51000	DIN	Germany	Casting
EN AC-51000	BS	British	Casting
EN AC-51000	UNI	Italy	Casting
EN AC-51000	AFNOR NF	France	Casting
EN AC-51000	UNE	Spain	Casting
EN AC-51000	SFS	Finland	Casting
EN AC-51000	BDS	Bulgaria	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com