

Material: ISO 3522 Al Mg9

Standard Specification for Aluminium and Aluminium Alloys

Group: Non-Ferrous Aluminium Alloy

Sub Group: ISO 3522 for Aluminium and Aluminium Alloys

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Silicon	Si %	2.500 max.	As-Cast	
Iron	Fe %	1.000 max.		
Copper	Cu %	0.100 max.		
Manganese	Mn %	0.550 max.		
Magnesium	Mg %	8.000 - 10.500		
Nickel	Ni %	0.100 max.		
Zinc	Zn %	0.250 max.		
Lead	Pb %	0.100 max.		
Tin	Sn %	0.100 max.		
Titanium	Ti %	0.200 max.		
Other	%	0.150 max.		
Aluminium	Al %	Balance		
-	-	-		
-	-	-		
-	-	-		

Mechanical Properties	
Tensile Strength in Mpa	200 min.
Yield Strength in Mpa	130 min.
Elongation in %	-
Reduction of Area in %	-
Hardness in HBW	70 min.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-51200	DIN	Germany	Casting
EN AC-51200	BS	British	Casting
EN AC-51200	ASME	USA	Casting
EN AC-51200	AFNOR NF	France	Casting
EN AC-51200	UNE	Spain	Casting
EN AC-51200	UNI	Italy	Casting
EN AC-51200	SFS	Finland	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com