

Material: ISO 3522 Al Si10Mg (Fe)

Standard Specification for Aluminium and Aluminium Alloys

Group: Non-Ferrous Aluminium Alloy

Sub Group: ISO 3522 for Aluminium and Aluminium Alloys

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Silicon	Si %	9.000 - 11.000	As-Cast	
Iron	Fe %	1.000 max.		
Copper	Cu %	0.100 max.		
Manganese	Mn %	0.550 max.		
Magnesium	Mg %	0.200 - 0.500		
Nickel	Ni %	0.150 max.		
Zinc	Zn %	0.150 max.		
Lead	Pb %	0.150 max.		
Tin	Sn %	0.050 max.		
Titanium	Ti %	0.200 max.		
Other	Ot%	0.150 max.	Mechanical Properties	
Aluminium	Al %	Balance	Tensile Strength in Mpa	240 min.
-	-	-	Yield Strength in Mpa	140 min.
-	-	-	Elongation in %	1 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HBW	70 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-43400	ASME	USA	Casting
EN AC-43400	DIN	Germany	Casting
EN AC-43400	BS	British	Casting
EN AC-43400	UNI	Italy	Casting
EN AC-43400	AFNOR NF	France	Casting
EN AC-43400	UNE	Spain	Casting
EN AC-43400	SFS	Finland	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com