

# Material: ISO 3522 Al Si11Cu3(Fe)

## Standard Specification for Aluminium and Aluminium Alloys

**Group:** Non-Ferrous Aluminium Alloy

**Sub Group:** ISO 3522 for Aluminium and Aluminium Alloys

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Casting

Chemical Composition			Heat Treatment	
Silicon	Si %	9.600 - 12.000	As-Cast	
Iron	Fe %	1.300 max.		
Copper	Cu %	1.500 - 3.500		
Manganese	Mn %	0.600 max.		
Magnesium	Mg %	0.350 max.		
Nickel	Ni %	0.450 max.		
Zinc	Zn %	1.700 max.		
Lead	Pb %	0.250 max.		
Tin	Sn %	0.250 max.		
Titanium	Ti %	0.250 max.		
Aluminium	Al %	Balance	Mechanical Properties	
0	0	0	Tensile Strength in Mpa	240 min.
0	0	-	Yield Strength in Mpa	140 min.
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HBW	80 min.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AA307	AS	Australia	Ingot and Casting
307	AS	Australia	Ingot and Casting
4520	IS	India	Ingot and Casting
ADC12	JIS	Japan	Ingot and Casting
ADC12Z	JIS	Japan	Ingot and Casting
383.0	AA	USA	Ingot and Casting
Al Si11Cu3(Fe)	JIS	Japan	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)