Material: ISO 3522 Al Si7Mg0.6

Standard Specification for Aluminium and Aluminium Alloys

Group: *Non-Ferrous Aluminium Alloy*
Sub Group: *ISO 3522 for Aluminium and Aluminium Alloys*
Application: *Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade*
Belongs to the Industry: *Casting*

Chemical Composition		
Silicon	Si %	6.500 - 7.500
Iron	Fe %	0.190 max.
Copper	Cu %	0.050 max.
Manganese	Mn %	0.100 max.
Magnesium	Mg %	0.450 - 0.700
Zinc	Zn %	0.070 max.
Titanium	Ti %	0.080 - 0.250
Other	Ot%	0.100 max.
Aluminium	Al %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or lution Anneling and Aging

Mechanical Properties	
Tensile Strength in Mpa	250 min.
Yield Strength in Mpa	210 min.
Elongation in %	1 min.
Reduction of Area in %	-
Hardness in HBW	85 min.
Impact in Joule	-

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
EN AC-42200	DIN	Germany	Casting
EN AC-42200	BS	British	Casting
EN AC-42200	UNE	Spain	Casting
EN AC-42200	UNI	Italy	Casting
EN AC-42200	SFS	Finland	Casting
EN AC-42200	AFNOR NF	France	Casting
EN AC-42200	MSZ	Hungary	Casting

Disclaimer: *All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.*

Customer Care: *+91-99090 45075 Email: info@icastllp.com*