

Material: ISO 3522 Al Si9Mg

Standard Specification for Aluminium and Aluminium Alloys

Group: Non-Ferrous Aluminium Alloy

Sub Group: ISO 3522 for Aluminium and Aluminium Alloys

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Silicon	Si %	9.000 - 10.000	As-Cast or Solution Anneling and Aging	
Iron	Fe %	0.190 max.		
Copper	Cu %	0.050 max.		
Manganese	Mn %	0.100 max.		
Magnesium	Mg %	0.250 - 0.450		
Zinc	Zn %	0.070 max.		
Titanium	Ti %	0.150 max.		
Other	Ot%	0.100 max.		
Aluminium	Al %	Balance		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	230 min.
			Yield Strength in Mpa	190 min.
			Elongation in %	2 min.
			Reduction of Area in %	-
			Hardness in HBW	75 min.
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-AISi9Mg	DIN	Germany	Casting
EN AC-AISi9Mg	BS	British	Casting
EN AC-AISi9Mg	UNE	Spain	Casting
EN AC-AISi9Mg	UNI	Italy	Casting
EN AC-AISi9Mg	SFS	Finland	Casting
EN AC-AISi9Mg	AFNOR NF	France	Casting
EN AC-AISi9Mg	MSZ	Hungary	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com