Material: ISO 3522 Al Zn10Si8Mg

Standard Specification for Aluminium and Aluminium Alloys

Group: *Non-Ferrous Aluminium Alloy*
Sub Group: *ISO 3522 for Aluminium and Aluminium Alloys*
Application: *Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade*
Belongs to the Industry: *Casting*

Chemical Composition		
Silicon	Si %	7.500 - 9.000
Iron	Fe %	0.300 max.
Copper	Cu %	0.100 max.
Manganese	Mn %	0.150 max.
Magnesium	Mg %	0.200 - 0.400
Zinc	Zn %	9.000 - 10.500
Titanium	Ti %	0.150 max.
Other	Ot%	0.150 max.
Aluminium	Al %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Aging

Mechanical Properties	
Tensile Strength in Mpa	220 min.
Yield Strength in Mpa	200 min.
Elongation in %	1 min.
Reduction of Area in %	-
Hardness in HBW	90 min.
Impact in Joule	-

Cross Reference Table			
Material	**Standard**	**Country**	**Grade Belong to the Industry**
EN AC- 71100	DIN	Germany	Casting
EN AC- 71100	BS	British	Casting
EN AC- 71100	ASME	USA	Casting
EN AC- 71100	AFNOR NF	France	Casting
EN AC- 71100	UNE	Spain	Casting
EN AC-71100	UNI	Italy	Casting
EN AC-71100	SFS	Finland	Casting

Disclaimer: *All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.*

Customer Care: *+91-99090 45075 Email: info@icastllp.com*