

Material: ISO 5832-12 Alloy 2

Standard Specification for Cobalt-Based alloy

Group: Non-Ferrous Cobalt Alloys

Sub Group: ISO 5832-12 Alloy 2 Cobalt-Based alloy

Application: Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.150 - 0.350	As-Cast or Annealing	
Chromium	Cr %	26.000 - 30.000		
Molybdenum	Mo %	5.000 - 7.000		
Nickel	Ni %	1.000 max.		
Iron	Fe %	0.750 max.		
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Nitrogen	N %	0.250 max.		
Cobalt	Co %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	897 min.
-	-	-	Yield Strength in Mpa	517 min.
-	-	-	Elongation in %	12 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
R31538	UNS	USA	Casting
F1537 Alloy 2	ASTM	USA	Casting
F799 Alloy 2	ASTM	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com