

Material: JIS H 5202 AC8A

Standard Specification for Aluminium Alloy Castings

Group: Non-Ferrous Aluminium Alloy

Sub Group: JIS H 5320 Aluminium Alloy Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.800 - 1.300	As-Cast	
Iron	Fe %	0.800 max.		
Magnesium	Mg %	0.700 - 1.300		
Manganese	Mn %	0.150 max.		
Nickel	Ni %	0.800 - 1.500		
Lead	Pb %	0.050 max.		
Silicon	Si %	11.000 - 13.500		
Tin	Sn %	0.050 max.		
Titanium	Ti %	0.020 max.		
Chromium	Cr %	0.100 max.		
Zinc	Zn %	0.150 max.		
Aluminium	Al %	Balance		
-	-	-		
-	-	-		
-	-	-		

Mechanical Properties	
Tensile Strength in Mpa	170 - 270
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in HB	85 - 110
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LM13	BS	British	Casting
A-S12UN	AFNOR NF	France	Casting
AA319	AS	Australia	Ingot and Casting
319	AS	Australia	Ingot and Casting
Alsi12NiCuMg	CSN	Czech Republic	Casting
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com