

## Material: JIS H 5202 AC8B

### Standard Specification for Aluminium Alloys for Casting

**Group:** Non-Ferrous Aluminium Alloy

**Sub Group:** JIS H 5202 Aluminium Alloys for Casting

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	2.000 - 4.000	As-Cast	
Iron	Fe %	1.000 max.		
Magnesium	Mg %	0.500 - 1.500		
Manganese	Mn %	0.500 max.		
Nickel	Ni %	0.100 - 1.000		
Lead	Pb %	0.100 max.		
Silicon	Si %	8.500 -10.500		
Tin	Sn %	0.100 max.		
Titanium	Ti %	0.200 max.		
Chromium	Cr %	0.100 max.		
Zinc	Zn %	0.500 max.	Mechanical Properties	
Aluminium	Al %	Balance	Tensile Strength in Mpa	215 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
AA305	AS	Australia	Ingot and Casting
305	AS	Australia	Ingot and Casting
LM26	BS	British	Ingot and Casting
332.0	AA	USA	Ingot and Casting
AC8C	JIS	Japan	Casting
AC8C	KS	Korea	Casting
A03320	UNS	USA	Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

**Customer Care:** +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)