

Material: JIS H 5302 ADC10Z

Standard Specification for Aluminium Alloy Casting

Group: Non-Ferrous Aluminium Alloy

Sub Group: JIS H 5302 Aluminium Alloy Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment			
Copper	Cu %	2.000 - 4.000	As-Cast			
Magnesium	Mg %	0.300 max.				
Silicon	Si %	7.500 - 9.500				
Iron	Fe %	1.300 max.				
Manganese	Mn %	0.500 max.				
Nickel	Ni %	0.500 max.				
Tin	Sn %	0.200 max.				
Lead	Pb %	0.200 max.				
Titanium	Ti %	0.300 max.				
Zinc	Zn %	3.000 max.				
Aluminium	Al %	Balance				
-	-	-			Mechanical Properties	
-	-	-	Tensile Strength in Mpa	180 min.		
-	-	-	Yield Strength in Mpa	-		
-	-	-	Elongation in %	1.5 min.		
-	-	-	Reduction of Area in %	-		
-	-	-	Hardness in BHN	-		
-	-	-	Impact in Joule	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
LM24	BS	British	Ingot and Casting
4420	IS	India	Ingot and Casting
AS313	AS	Australia	Ingot and Casting
BB325	AS	Australia	Ingot and Casting
CA313	AS	Australia	Ingot and Casting
380.0	AA	USA	Ingot and Casting
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com