

Material: JIS SCH 22

Standard Specification for Heat-Resistant Cast Steels and Alloys for General Applications

Group: Ferrous Stainless Steel Alloys

Sub Group: JIS SCH 22 Heat-Resistant Cast Steels and Alloys for General Applications

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.350 - 0.450
Silicon	Si %	1.750 max.
Manganese	Mn %	1.500 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.040 max.
Chromium	Cr %	23.000 - 27.000
Nickel	Ni %	19.000 - 22.000
Molybdenum	Mo %	0.500 max.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
Solution Annealing

Mechanical Properties	
Tensile Strength in Mpa	440 min.
Yield Strength in Mpa	235 min.
Elongation in %	8 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA-351 Grade HK 40	ASME	USA	Casting
310 C 45	BS	British	Casting
40 CrNiSi 25-20	MSZ	Hungary	Casting
1.4848	DIN	Germany	Casting
A-608 Grade HK 40	ASME	USA	Casting
A-567 Grade HK 40	ASTM	USA	Casting
A351 HT30	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India