

Material: JIS SCPH 11

Standard Specification for Low Alloy Steel

Group: Ferrous Mild Steel Alloys

Sub Group: JIS SCPH 11 Low Alloy Steel

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 max.	Normalizing or Annealing or Hardening + Tempering	
Silicon	Si %	0.600 max.		
Manganese	Mn %	0.500 - 0.800		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.040 max.		
Molybdenum	Mo %	0.450 - 0.650		
Chromium	Cr %	0.300 max.		
Nickel	Ni %	0.500 max.		
Tungsten	W %	0.100 max.		
Iron	Fe %	Balance	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	450 min.
-	-	-	Yield Strength in Mpa	245 min.
-	-	-	Elongation in %	22 min.
-	-	-	Reduction of Area in %	35 min.
-	-	-	Hardness in BHN	-
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SA217 WC1	ASME	USA	Casting
G20 Mo 5	EN	European Union	Casting
J12524	UNS	USA	Casting
A352 LC1	ASTM	USA	Casting
G 20 MO5	DIN	Germany	Casting
G 20 MO5	UNI	Italy	Casting
A217 Grade WC1	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com