

Material: JIS SCS 21

Standard Specification for Austenitic Stainless Steel Castings for General Application

Group: Ferrous Stainless Steel Alloys

Sub Group: G 5121 Austenitic Stainless Steel Castings for General Application

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.080 max.
Silicon	Si %	2.000 max.
Manganese	Mn %	2.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.040 max.
Chromium	Cr %	18.000 - 21.000
Nickel	Ni %	9.000 - 12.000
Iron	Fe %	Balance
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
Solutionizing: 1030-1150°C, rapid cooling.	

Mechanical Properties	
Tensile Strength in Mpa	480 min.
Yield Strength in Mpa	205 min.
Elongation in %	28 min.
Reduction of Area in %	-
Hardness in HB	183 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4552	EN	European Union	Casting
347 C 17	BS	British	Casting
GX 5 CrNiNb 19-11	DIN	Germany	Casting
SA-351 Grade CF8C	ASME	USA	Casting
A743 CF8C	ASTM	USA	Casting
A744 CF8C	ASTM	USA	Casting
A351 CH8C	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India