

# Material: JIS SUS 434

## Standard Specification for Chromium and Chromium-Nickel Stainless Steel Plate, Sheet and Strip for Pressure Vessels and for General Applications

**Group:** Ferrous Stainless Steel Alloys

**Sub Group:** JIS SUS 434 Chromium and Chromium-Nickel Stainless Steel for Pressure Vessels and for General Applications

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Steel, Wire and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.120 max.	Annealing or Hardening + Tempering	
Silicon	Si %	1.000 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.030 max.		
Chromium	Cr %	16.000 - 18.000		
Molybdenum	Mo %	0.750 - 1.250		
Nickel	Ni %	0.600 max.		
Iron	Fe %	Balance		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
-	-	-		
Mechanical Properties				
			Tensile Strength in Mpa	413.7 min.
			Yield Strength in Mpa	206.8 min.
			Elongation in %	-
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
A240 UNS S43400	ASTM	USA	Steel, Plate, Sheet and Strip
S43400	UNS	USA	Steel
434 S 20	BS	British	Steel and Wire
51434	SAE	USA	Steel
A651 TP 434	ASTM	USA	Steel and Tube
A959 Type 434	ASTM	USA	Steel
STS 434	KS	Korea	Steel, Wire and Rod

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India