

Material: KS D2320 CACIn202

Standard Specification for Copper Alloys Ingot and Casting

Group: Non-Ferrous Copper Alloy

Sub Group: KS D2320 Copper Alloys Ingot and Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Ingot and Casting

Chemical Composition		
Aluminium	Al %	0.500 max.
Iron	Fe %	0.600 max.
Nickel	Ni %	1.000 max.
Lead	Pb %	0.500 - 3.000
Tin	Sn %	0.100 max.
Copper	Cu %	65.000 - 70.000
Zinc	Zn %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast

Mechanical Properties	
Tensile Strength in Mpa	207 min.
Yield Strength in Mpa	76 min.
Elongation in %	20 min.
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C85400	UNS	USA	Rod, Bar, Tube and Shapes
B30 C85400	ASTM	USA	Ingot and Casting
B271 C85400	ASTM	USA	Casting
B584 C85400	ASTM	USA	Casting
C85400	SAE	USA	Casting
CA854	SAE	USA	Casting
C85400	AS	Australia	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India