

Material: KS D2320 CACIn303

Standard Specification for Copper Alloy Ingot for Casting

Group: Non-Ferrous Copper Alloy

Sub Group: KS CACIn203 Copper Alloy Ingot for Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	3.000 - 5.000	As-Cast	
Iron	Fe %	2.000 - 4.000		
Manganese	Mn %	2.500 - 5.000		
NiCkel	Ni %	0.500 max.		
Lead	Pb %	0.200 max.		
Tin	Sn %	0.500 max.		
Copper	Cu %	60.000 - 65.000		
Zinc	Zn %	Balance		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	621 min.
			Yield Strength in Mpa	310 min.
			Elongation in %	18 min.
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C86200	UNS	USA	Rod, Bar, Tube and Shapes
B147-8B	ASTM	USA	Casting
B271 C86200	ASTM	USA	Casting
CA862	SAE	USA	Casting
SAE 430A	SAE	USA	Casting
SB-505 C86200	ASME	USA	Casting
SB-584 C86200	ASME	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com