

# Material: MS 1795 SWRCH22A

## Standard Specification for Carbon Steel Wire Rods for Cold Heading and Cold Forging

**Group:** Ferrous Mild Steel Alloys

**Sub Group:** MS 1795 SWRCH22A Carbon Steel Wire Rods for Cold Heading and Cold Forging

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Wire Rod and Forging

Chemical Composition		
Carbon	C %	0.180 - 0.230
Silicon	Si %	0.100 max.
Manganese	Mn %	0.700 - 1.000
Phosphorus	P %	0.030 max.
Sulphur	S %	0.035 max.
Aluminium	Al %	0.020 min.
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Raw or Normalizing or Annealing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	580 max.
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	45 min.
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
SWRCH 22A	JIS	Japan	Wire Rod and Forging
SWCH 22A	JIS	Japan	Wire Rod and Forging
C20C	ISO	International	Wire Rod and Forging
SWRCH22A	KS	Korea	Wire Rod and Forging
-	-	-	-
-	-	-	-
-	-	-	-

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India