

Material: MSZ EN 1706 AC-44000

Standard Specification for Aluminium and Aluminium Alloys - Castings

Group: Non-Ferrous Aluminium Alloy

Sub Group: MSZ EN 1706 Aluminium and Aluminium Alloys - Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	0.100 max.	As-Cast	
Iron	Fe %	0.650 max.		
Magnesium	Mg %	0.100 max.		
Manganese	Mn %	0.500 max.		
Nickel	Ni %	0.050 max.		
Silicon	Si %	8.000 - 11.000		
Lead	Pb %	0.050 max.		
Tin	Sn %	0.050 max.		
Titanium	Ti %	0.150 max.		
Zinc	Zn %	0.150 max.		
Other	Ot%	0.150 max.		
Aluminium	Al %	Balance		
-	-	-		
-	-	-		
-	-	-		

Mechanical Properties	
Tensile Strength in Mpa	170 - 220
Yield Strength in Mpa	80 - 120
Elongation in %	2 - 5
Reduction of Area in %	-
Hardness in HB	50 - 55
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-44000	ASME	USA	Casting
EN AC-44000	DIN	Germany	Casting
EN AC-44000	UNE	Spain	Casting
EN AC-44000	SFS	Finland	Casting
Al Si9	ISO	International	Casting
EN AC-44000	AFNOR NF	France	Casting
EN AC-44000	BDS	Bulgaria	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com