

Material: MSZ EN 1706 AC-48100

Standard Specification for Aluminium and Aluminium Alloys - Casting

Group: Non-Ferrous Aluminium Alloy

Sub Group: MSZ EN 1706 Aluminium and Aluminium Alloys - Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Copper	Cu %	4.000 - 5.000	As-Cast	
Iron	Fe %	1.300 max.		
Magnesium	Mg %	0.250 - 0.650		
Manganese	Mn %	0.500 max.		
Nickel	Ni %	0.300 max.		
Silicon	Si %	16.000 - 18.000		
Tin	Sn %	0.150 max.		
Titanium	Ti %	0.250 max.		
Zinc	Zn %	1.500 max.		
Other	Ot%	0.250 max.		
Aluminium	Al %	Balance	Mechanical Properties Tensile Strength in Mpa 200 - 295 Yield Strength in Mpa 160 - 260 Elongation in % 1 min. Reduction of Area in % - Hardness in HB 75 min. Impact in Joule -	
-	-	-		
-	-	-		
-	-	-		
-	-	-		

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
EN AC-48100	DIN	Germany	Casting
EN AC-48100	ASME	USA	Casting
EN AC-48100	UNI	Italy	Casting
EN AC-48100	AFNOR NF	France	Casting
EN AC-48100	UNE	Spain	Casting
EN AC-48100	SFS	Finland	Casting
B 390	AA	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com