

Material: MSZ NCMo 6 Z

Standard Specification for Mild Steel Alloys Bar and Rod

Group: Ferrous Mild Steel Alloys

Sub Group: MSZ NCMo 6 Z Mild Steel Alloys Bar and Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar and Rod

Chemical Composition			Heat Treatment	
Carbon	C %	0.260 - 0.340	As Raw or Annealing or Normalizing or Hardening and Tempering	
Silicon	Si %	0.400 max.		
Manganese	Mn %	0.300 - 0.600		
Phosphorus	P %	0.035 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	1.800 - 2.200		
Molybdenum	Mo %	0.300 - 0.500		
Nickel	Ni %	1.800 - 2.200		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	930 - 1330
-	-	-	Yield Strength in Mpa	750 min.
-	-	-	Elongation in %	10 min.
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in BHN	255 max.
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
30CrNiMo8	EN	European Union	Bar and Rod
1.658	EN	European Union	Bar and Rod
P 1000 - 30CrNiMo8	AFNOR NF	France	Bar and Rod
30 CND 8	AFNOR NF	France	Bar and Rod
NCMo 6	MSZ	Hungary	Bar and Rod
30CrNiMo8	ISO	International	Bar and Rod
31 CrNiMo 8	ISO	International	Bar and Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com