

Material: NBN 1.5532

Standard Specification for Mild Steel Alloys Bar and Rod

Group: Ferrous Mild Steel Alloys

Sub Group: NBN 1.5532 Mild Steel Alloys Bar and Rod

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bar and Rod

Chemical Composition		
Carbon	C %	0.360 - 0.420
Silicon	Si %	0.400 max.
Manganese	Mn %	1.150 - 1.450
Phosphorus	P %	0.025 max.
Sulphur	S %	0.035 max.
Boron	B %	0.0008 - 0.0050
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Raw or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	850 - 1250
Yield Strength in Mpa	700 min.
Elongation in %	12 min.
Reduction of Area in %	50 min.
Hardness in HRC	45 max.
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
38MnB5	EN	European Union	Bar and Rod
1.5532	EN	European Union	Bar and Rod
38 MB 5	AFNOR NF	France	Bar, Wire and Rod
39MnB5	ISO	International	Bar and Rod
38 MB 5	NBN	Belgium	Bar and Rod
1.5532	PN	Poland	Bar and Rod
38 MB 5	PN	Poland	Bar and Rod

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India