

# Material: NBN 1.7189

## Standard Specification for Mild Steel Alloys Bar and Rod

**Group:** Ferrous Mild Steel Alloys

**Sub Group:** NBN 1.7189 Mild Steel Alloys Bar and Rod

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries

**Grade Belongs to the Industry:** Bar and Rod

Chemical Composition		
Carbon	C %	0.360 - 0.420
Silicon	Si %	0.400 max.
Manganese	Mn %	1.400 - 1.700
Phosphorus	P %	0.025 max.
Sulphur	S %	0.035 max.
Chromium	Cr %	0.300 - 0.600
Boron	B %	0.0008 - 0.0050
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Raw or Annealing or Normalizing or Hardening and Tempering

Mechanical Properties	
Tensile Strength in Mpa	1000 - 1350
Yield Strength in Mpa	800 min.
Elongation in %	12 min.
Reduction of Area in %	50 min.
Hardness in BHN	255 max.
Impact in Joule	40 J @ RT

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
39MnCrB6-2	EN	European Union	Bar and Rod
1.7189	EN	European Union	Bar and Rod
39MnCrB6-2	ISO	International	Bar and Rod
1.7189	AFNOR NF	France	Bar and Rod
39MnCrB6-2	AFNOR NF	France	Bar and Rod
1.7189	BS	British	Bar and Rod
39MnCrB6-2	BS	British	Bar and Rod

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India