

Material: NBR 15975 384.0

Standard Specification for Aluminium Alloys for Casting

Group: Non-Ferrous Aluminium Alloy

Sub Group: NBR 15975 Aluminium Alloys for Casting

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition		
Copper	Cu %	3.000 - 4.504
Iron	Fe %	1.300 max.
Magnesium	Mg %	0.100 max.
Manganese	Mn %	0.500 max.
Nickel	Ni %	0.500 max.
Silicon	Si %	10.500 - 12.000
Tin	Sn %	0.350 max.
Zinc	Zn %	3.000 max.
Other	Ot%	0.500 max.
Aluminium	Al %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
As-Cast	

Mechanical Properties	
Tensile Strength in Mpa	330 min.
Yield Strength in Mpa	165 min.
Elongation in %	2.5 min.
Reduction of Area in %	-
Hardness in HB	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
B 275 383.0	ASTM	USA	Casting
AA335	AS	Australia	Ingot and Casting
A03830	UNS	USA	Ingot and Casting
A03830	SAE	USA	Ingot and Casting
384	AA	USA	Casting
383.0	NMX	Maxico	Casting
SC102A	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com