

Material - ONORM EN 1982 CuZn35Mn2Al1Fe1-B

Standard Specification for Copper and Copper Alloys - Ingots and Castings

Group - Non-Ferrous Copper Alloy

Sub Group - ONORM EN 1982 Copper and Copper Alloys - Ingots and Castings

Application - Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry - Ingot and Casting

Chemical Composition		
Aluminium	Al %	0.700 - 2.200
Iron	Fe %	0.500 - 1.800
Manganese	Mn %	0.500 - 2.500
Nickel	Ni %	6.000 max.
Phosphorus	P %	0.020 max.
Lead	Pb %	0.500 max.
Antimony	Sb %	0.080 max.
Silicon	Si %	0.100 max.
Tin	Sn %	0.800 max.
Cu + Ni	Cu%+Ni%	56.000 - 64.000
Zinc	Zn %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast

Mechanical Properties	
Tensile Strength in Mpa	450 - 500
Yield Strength in Mpa	170 :-00
Elongation in %	:8 - 20
Reduction of Area in %	-
Hardness in HB	110 - 120
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC765S	BS	British	Ingot and Casting
CB765S	DIN	Germany	Ingot and Casting
CB765S	BDS	Bulgaria	Ingot and Casting
CB765S	CSN	Czech Republic	Ingot and Casting
CuZn35Mn2Al1Fe1-B	AFNOR NF	France	Ingot and Casting
CuZn35Mn2Al1Fe1-B	UNE	Spain	Ingot and Casting
CuZn35Mn2Al1Fe1-B	MSZ	Hungary	Ingot and Casting

Further any inquiry to discuss with Gravity Cast Pvt. Ltd. – Gravity Group of Companies team member Call on +918469160029, or email marketing@gravitycastindia.com

All information in our data sheets and website is indicative only and is not intended to be a substitute for the full specification from which it is extracted. It is intended to provide typical values to allow comparison between metal alloy option rather than a definitive statement of mechanical performance or suitability for a particular application as these will vary with temperature, product type and product application. It is presented apart from contractual obligations and does not constitute any



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India

guarantee of properties or of processing or application possibilities in individual cases. Our warranties and liabilities are stated exclusively in our terms of business. **Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com

ICAST ALLOYS LLP



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India