

Material: ONORM EN-GJS-900-2

Standard Specification For Spheroidal Graphite Cast Irons Castings

Group: Ferrous SG Iron / Ductile Iron Alloys

Sub Group: ONORM EN-GJS-900-2 Spheroidal Graphite Cast Irons Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	-
Silicon	Si %	-
Manganese	Mn %	-
Phosphorus	P %	-
Sulphur	S %	-
Chromium	Cr %	-
Nickel	Ni %	-
Copper	Cu %	-
Iron	Fe %	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast

Mechanical Properties	
Tensile Strength in Mpa	900 min.
Yield Strength in Mpa	600 min.
Elongation in %	2 min.
Reduction of Area in %	-
Hardness in BHN	270 - 360
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
JS 900-2	ISO	International	Casting
JS 900-2	AS	Australia	Casting
5.3302	EN	European Union	Casting
EN-GJS-900-2	UNI	Italy	Casting
SG 900 I 2	IS	India	Casting
EN-JS1090	UNE	Spain	Casting
5.3302	BS	British	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India