

Material: PN CuSn7Zn4Pb7-B

Standard Specification for Copper and Copper Alloy Ingot and Castings

Group: Non Ferrous Copper Alloys

Sub Group: PN CuSn7Zn4Pb7-B Copper and Copper Alloy Ingot and Castings

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Ingot and Casting

Chemical Composition		
Silicon	Si %	0.010 max.
Lead	Pb %	5.200 - 8.000
Iron	Fe %	0.200 max.
Tin	Sn %	6.200 - 8.000
Zinc	Zn %	2.300 - 5.000
Nickel	Ni %	2.000 max.
Aluminium	Al %	0.010 max.
Sulphur	S %	0.080 max.
Antimony	Sb %	0.300 max.
Phosphorus	P %	0.030 max.
Cu + Ni	Cu% + Ni%	81.000 - 85.000
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As Cast

Mechanical Properties	
Tensile Strength in Mpa	-
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CuSn7Zn4Pb7-B	DIN	Germany	Ingot and Casting
CB493K	ONORM	Australia	Ingot and Casting
CB493K	UNI	Italy	Ingot and Casting
CuSn7Zn4Pb7-B	UNI	Italy	Ingot and Casting
CuSn7Zn4Pb7-B	BS	British	Ingot and Casting
CB493K	BS	British	Ingot and Casting
CB493K	PN	Poland	Ingot and Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India