

# Material: PN EN 1982 CB752S

## Standard Specification for Copper and Copper Alloys - Ingots and Castings

**Group:** Non-Ferrous Copper Alloy

**Sub Group:** PN 1982 Copper and Copper Alloys - Ingots and Castings

**Application:** Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

**Belongs to the Industry:** Ingot and Casting

Chemical Composition		
Aluminium	Al %	0.300 - 0.700
Arsenic	As %	0.040 - 0.120
Iron	Fe %	0.300 max.
Manganese	Mn %	0.100 max.
Nickel	Ni %	0.200 max.
Lead	Pb %	1.500 - 2.100
Antimony	Sb %	0.040 - 0.120
Silicon	Si %	0.020 max.
Tin	Sn %	0.300 max.
Copper	Cu %	61.500 - 65.000
Zinc	Zn %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast

Mechanical Properties	
Tensile Strength in Mpa	-
Yield Strength in Mpa	-
Elongation in %	-
Reduction of Area in %	-
Hardness in BHN	-
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
CC752S	BS	British	Ingot and Casting
CB752S	UNI	Italy	Ingot and Casting
CB752S	UNE	Spain	Ingot and Casting
CB752S	CSN	Czech Republic	Ingot and Casting
CB752S	BDS	Bulgaria	Ingot and Casting
CB752S	ONORM	Australia	Ingot and Casting
CB752S	MSZ	Hungary	Ingot and Casting

**Disclaimer:** All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: [info@icastllp.com](mailto:info@icastllp.com)



+91-99090 45075



[info@icastllp.com](mailto:info@icastllp.com)



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India