

Material: PN LH 19 N 14 G

Standard Specification for Heat-Resisting Cast Steel Alloy

Group: Ferrous Stainless Steel Alloys

Sub Group: PN LH 19 N 14 G Heat-Resisting Cast Steel Alloy

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Carbon	C %	0.250 max.	Solution Annealing	
Silicon	Si %	1.500 max.		
Manganese	Mn %	1.000 max.		
Phosphorus	P %	0.040 max.		
Sulphur	S %	0.035 max.		
Chromium	Cr %	18.000 - 20.000		
Nickel	Ni %	13.000 - 15.000		
Iron	Fe %	Balance		
-	-	-	Mechanical Properties	
-	-	-	Tensile Strength in Mpa	420 min.
-	-	-	Yield Strength in Mpa	-
-	-	-	Elongation in %	-
-	-	-	Reduction of Area in %	-
-	-	-	Hardness in HB	250 - 350
-	-	-	Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
1.4832	DIN	Germany	Casting
J92604	UNS	USA	Casting
19 Cr12 Ni 4 Mn	Common	-	Casting
S30409	UNS	USA	General Corrosive Service
A 297 HG10MnN	ASTM	USA	Casting
A743 HG10MnN	ASTM	USA	Casting
A351 HG10MnN	ASTM	USA	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com