

Material: SAE 1008

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, To Wire Rods, Plates, Strip, Sheets, Tubing

Group: Ferrous Mild Steel Alloys

Sub Group: SAE 1008 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Chemical Composition			Heat Treatment
Carbon	C %	0.100 max.	As Raw or Annealing or Normalizing or Hardening and Tempering
Manganese	Mn %	0.300 - 0.500	
Phosphorus	P %	0.040 max.	
Sulphur	S %	0.050 max.	
Chromium	Cr %	0.070 max.	
Copper	Cu %	0.200 max.	
Molybdenum	Mo %	0.050 max.	
Nickel	Ni %	0.150 max.	
Silicon	Si %	0.200 max.	
Iron	Fe %	Balance	
-	-	-	
-	-	-	
-	-	-	
-	-	-	
-	-	-	

Mechanical Properties		
Tensile Strength in Mpa	303 - 340	
Yield Strength in Mpa	170 min.	
Elongation in %	20 min.	
Reduction of Area in %	45 - 55	
Hardness in HB	86 - 95	
Impact in Joule	-	

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10080	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1008	AISI	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 1040 1008	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 108 Grade 1008	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 29 1008	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 29 M1008	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
A 510 1008	ASTM	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India