

Material: SAE 1042

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Group: Ferrous Mild Steel Alloys

Sub Group: SAE 1042 Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition		
Carbon	C %	0.400 - 0.470
Manganese	Mn %	0.600 - 0.900
Phosphorus	P %	0.030 max.
Sulphur	S %	0.035 max.
Boron	B %	0.0005 - 0.003
Chromium	Cr %	0.150 max.
Copper	Cu %	0.200 max.
Molybdenum	Mo %	0.060 max.
Nickel	Ni %	0.200 max.
Lead	Pb %	0.150 - 0.350
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
As Raw or Annealing or Normalizing or Hardening and Tempering	

Mechanical Properties	
Tensile Strength in Mpa	550 - 179
Yield Strength in Mpa	300 min.
Elongation in %	12 min.
Reduction of Area in %	35 - 45
Hardness in HB	163 - 179
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10420	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1042	AISI	USA	Bar
A 1040 1042	ASTM	USA	Steel
A 29 1042	ASTM	USA	Bar
A 510 1042	ASTM	USA	Wire Rod
A 576 10L42	ASTM	USA	Steel and Bar
A 830 1042	ASTM	USA	Plate and Steel

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India