

Material: SAE 1060

Standard Specification For Carbon Steel Compositions For Forging To Hot-Rolled And Cold-Finished Steel

Group: Ferrous Mild Steel Alloys

Sub Group: SAE 1060 Carbon Steel Compositions For Forging To Hot-Rolled Steel

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries

Grade Belongs to the Industry: Steel

Chemical Composition		
Carbon	C %	0.550 - 0.650
Manganese	Mn %	0.600 - 0.900
Phosphorus	P %	0.030 max.
Sulphur	S %	0.035 max.
Boron	B %	0.0005 - 0.003
Copper	Cu %	0.200 min.
Chromium	Cr %	0.150 max.
Molybdenum	Mo %	0.060 max.
Nickel	Ni %	0.200 max.
Lead	Pb %	0.150 - 0.350
Iron	Fe %	Balance
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment	
As Raw or Annealing or Normalizing or Hardening and Tempering	

Mechanical Properties	
Tensile Strength in Mpa	620 - 680
Yield Strength in Mpa	370 min.
Elongation in %	10 min.
Reduction of Area in %	30 - 45
Hardness in HB	183 - 201
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
G10600	UNS	USA	Bars, Wire Rods, Plates, Strip, Sheets and Tubing
1060	AISI	USA	Steel and Tubing
A 1040 1060	ASTM	USA	Steel
A 29 1060	ASTM	USA	Stee and Bar
A 510 1060	ASTM	USA	Wire Rod, Round Rod and Steel
A 513 Grade 1060	ASTM	USA	Steel and Tubing
A 576 10L60	ASTM	USA	Bar

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India