

Material: SAE 5378

Standard Specification for Cobalt-Based alloy

Group: Non-Ferrous Cobalt Alloys

Sub Group: SAE 5378 Cobalt-Based alloy

Application: Intended for Valve, Pump, General Engineering, Automotive, Medical and other Industries

Grade Belongs to the Industry: Casting

Chemical Composition		
Carbon	C %	0.350 - 0.450
Silicon	Si %	1.000 max.
Manganese	Mn %	1.000 max.
Chromium	Cr %	23.000 - 26.000
Nickel	Ni %	30.000 - 35.000
Molybdenum	Mo %	4.500 - 6.500
Iron	Fe %	2.000 max.
Phosphorus	P %	0.040 max.
Sulphur	S %	0.030 max.
Cobalt	Co %	Balance
-	-	-
-	-	-
-	-	-
-	-	-
-	-	-

Heat Treatment
As-Cast or Annealing

Mechanical Properties	
Tensile Strength in Mpa	330 min.
Yield Strength in Mpa	-
Elongation in %	12 min.
Reduction of Area in %	-
Hardness in HRC	22 min
Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
Stellite 27	Gravity	India	Casting
R30027	UNS	USA	Casting
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-
-	-	-	-

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com



+91-99090 45075



info@icastllp.com



ICAST ALLOYS LLP, Plot 2527, Road H1, Kranti Gate, GIDC Metoda, Lodhika, Rajkot-360021, Gujarat, India