

Material: SAE 620

Standard Specification for Cast Copper Alloys

Group: Non-Ferrous Copper Alloy

Sub Group: SAE J462 Cast Copper Alloys

Application: Intended for Valve, Pump, General Engineering, Automotive and Other Industries Grade

Belongs to the Industry: Casting

Chemical Composition			Heat Treatment	
Aluminium	Al %	0.005 max.	As-Cast	
Iron	Fe %	0.150 max.		
Nickel	Ni %	1.000 max.		
Lead	Pb %	0.300 max.		
Tin	Sn %	7.500 - 9.000		
Zinc	Zn %	3.000 - 5.000		
Copper	Cu %	86.000 - 89.000		
-	-	-		
-	-	-		
-	-	-		
			Mechanical Properties	
			Tensile Strength in Mpa	276 - 303
			Yield Strength in Mpa	152 min.
			Elongation in %	18 - 20
			Reduction of Area in %	-
			Hardness in BHN	-
			Impact in Joule	-

Cross Reference Table			
Material	Standard	Country	Grade Belong to the Industry
C90300	UNS	USA	Rod, Bar, Tube and Shapes
B30 C90300	ASTM	USA	Ingot and Casting
B505 C89320	ASTM	USA	Casting
CA903	SAE	USA	Casting
SB-505 C90300	ASME	USA	Casting
SB-584 C90300	ASME	USA	Casting
CACIn402	KS	Korea	Casting

Disclaimer: All information displayed in our data sheets are for reference purpose only and are sole property of their respective owners. Information and or material are used for educational purposes only. Data at actual may vary at actual and case to case basis. ICAST Alloys LLP does not guarantee validity of these parameters. Warranties and liabilities are exclusive to our terms and conditions of business.

Customer Care: +91-99090 45075 Email: info@icastllp.com